

## MATERIAL SAFETY DATA SHEET

### Poly Acryl SA 87

Revision date:

Revision NO: 0

Edition Date:

Aug. 2010

Page:

1/5

#### - IDENTIFICATION OF THE SUBSTANCE/PREPARATION AND OF THE COMPANY/UNDERTAKING

##### Product information

Trade name : **Poly Acryl SA 87**

Company : No:771,zereshki alley tajbakhsh street , 25 km karaj special road  
,Tehran-Iran

Telephone : (+98 263) 6102231-2 , (+98 263) 6102299

Telefax : : (+98 263) 6102023

Email address : [info@awachimie.com](mailto:info@awachimie.com)

Use of the Substance : It is used in constructions. Also, this resin is very suitable for manufacturing sealing coatings, plasters, tile adhesive, roof coating, and a lot of kinds of coatings which are expected to have high resistance and Laminating adhesive.

#### - PHYSICAL AND CHEMICAL PROPERTIES

Physical state liquid

Colour milky

Odour faint

Total solid (ASTM D 2369) 50±1%

Viscosity (23°C, Brookfield RV #5/RPM 10) 180-400 P

pH (ASTM D 1293) 7.5-9

MFFT (ISO 2811) <0°C

Density (ASTM D1475 ) 1/04±0.02g/cm<sup>3</sup>

Water solubility dilutable

#### - FIRST AID MEASURES

##### General advice

Remove contaminated or saturated clothing.

##### Skin contact

Wash off with plenty of water and soap immediately.

**Eye contact**

Rinse with plenty of water immediately, seek medical advice if necessary.

**Ingestion.**

Seek medical advice.

**- HANDLING AND STORAGE**

**Handling**

**Safe handling advice**

Avoid contact with skin and eyes.

Application, processing: Provide good ventilation or extraction.

**Advice on protection against fire and explosion**

Normal measures for preventive fire protection.

**Storage**

**Requirements for storage areas and containers**

Keep container tightly closed.

Protect from frost.

**- OTHER INFORMATION**

NOTICE: Awa chimie believes the information contained here is accurate. However, Awa chimie makes no warranty, expressed or implied, regarding the accuracy of this data or the results to be obtained by the use thereof. , Awa chimie assumes no responsibility for injury from the use of the product described herein.